

IPC-4103 /17 UL - File Number E41625

I-Tera® MT40 laminate materials exhibit exceptional electrical properties which are very stable over a broad frequency and temperature range.

PRODUCT FEATURES

Industry Recognition

- UL File Number: E41625
- RoHS Compliant

Performance Attributes

- CAF resistant
- Lead-free assembly compatible

Processing Advantages

- FR-4 process compatible
- Dimensional stability
- Multiple reflow capable
- Multiple lamination cycles

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- 10, 20, 30, 60 mil (0.25, 0.51, 0.76, 1.5 mm)

Copper Foil Type

- HTE Grade 3
- HVLP (VLP2) ≤ 2.5 micron Rz JIS
- RTF (Reverse Treat Foil)
- Embedded resistor foil

Copper Weight

- ½, 1 and 2 oz (18, 35 and 70 μm) available
- Thinner copper foil available

Glass Fabric Availability

- Square weave glass
- Mechanically spread glass

I-Tera MT40 is suitable for many of today's high-speed digital and RF/microwave printed circuit designs. I-Tera MT40 features a dielectric constant (DK) that is stable between -40°C and +140°C up to W-band frequencies. In addition, I-Tera MT40 offers a very low dissipation factor (Df) of 0.0028 - 0.0035 making it a cost-effective alternative to PTFE and other commercial microwave and high-speed digital laminate materials.

I-Tera MT40 laminate materials are currently being offered in both laminate and prepreg form in typical thicknesses and standard panel sizes. This provides a complete materials solution package for high-speed digital multilayer, hybrid, RF/microwave, multilayer and double-sided printed circuit designs. I-Tera MT40 does not require any special through hole treatments commonly needed when processing PTFE-based laminate materials.

PRODUCT ATTRIBUTES



HIGH THERMAL
RELIABILITY



RADIO FREQUENCY
& MICROWAVE

TYPICAL MARKET APPLICATIONS



AUTOMOTIVE &
TRANSPORTATION



RADIO FREQUENCY
& MICROWAVE



AEROSPACE
& DEFENSE



MEDICAL, INDUSTRIAL
& INSTRUMENTATION

ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler,
AZ 85226 Phone: 480-893-6527
Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd. 12/F,
Kin Sang Commercial Centre,
49 King Yip Street, Kwun Tong,
Kowloon,
Hong Kong Phone: 852-2418-1318
Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren,
Germany Phone: 49-2421-8080
Fax: 49-2421-808164

Typical Values Table

Property	Typical Value	Units		Test Method
		Metric (English)		IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC	215	°C		2.4.25C
Glass Transition Temperature (Tg) by DMA	230	°C		2.4.24.4
Glass Transition Temperature (Tg) by TMA	210	°C		2.4.24C
Decomposition Temperature (Td) by TGA @ 5% weight loss	360	°C		2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	>60	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	55 290 2.8	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	12	ppm/°C	2.4.24C
Thermal Conductivity		0.61	W/m·K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 10 GHz B. @ 10 GHz C. @ 10 GHz D. @ 10 GHz	3.38 3.45 3.60 3.75	—	2.5.5.5
Df, Loss Tangent	A. @ 10 GHz B. @ 10 GHz C. @ 10 GHz D. @ 10 GHz	0.0028 0.0031 0.0035 0.0035	—	Bereskin Stripline
Volume Resistivity	C-96/35/90	1.33×10^7	MΩ-cm	2.5.17.1
Surface Resistivity	C-96/35/90	1.33×10^5	MΩ	2.5.17.1
Dielectric Breakdown		45.4	kV	2.5.6B
Arc Resistance		139	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		45 (1133)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	1 oz. EDC foil	1.0 (5.7)	N/mm (lb/inch)	2.4.8C
Flexural Strength	A. Length direction B. Cross direction	490 (71.0) 400 (58.0)	MPa (kpsi)	2.4.4B
Tensile Strength	A. Length direction B. Cross direction	269 (39.0) 241 (35.0)	MPa (kpsi)	ASTM D3039
Poisson's Ratio	A. Length direction B. Cross direction	0.234 0.222	—	ASTM D3039
Moisture Absorption		0.1	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		130	°C	UL 796

NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected units for Flexural and Tensile Strength - 8/18

C: Change MOT to RTI 5/19

D: Changed VLP2 to HVLP to align with common industry terms 4/21

E: Changed TMA Tg to 210C, DSC Tg to 215C and added DMA at 230C based on long term data 9/22

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.